

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
7 October 2004 (07.10.2004)

PCT

(10) International Publication Number
WO 2004/085341 A1

(51) International Patent Classification⁷: C04B 35/66,
35/18, F27D 1/16, C10B 29/06, C21C 5/44

TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

(21) International Application Number:
PCT/BE2004/000045

(22) International Filing Date: 29 March 2004 (29.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03447065.8 27 March 2003 (27.03.2003) EP

(71) Applicant (for all designated States except US): PRE-
MIER REFRACTORIES (BELGIUM) S.A. [BE/BE];
Rue de la Rivière, 100, B-7330 Saint-Ghislain (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): SABRE, Serge
[FR/FR]; Place Ambroise Croizat 25, F-62640 Mon-
tigny-en-Gohelle (FR). JONAS, Christophe [BE/BE];
Rue des Aubépines 5, B-7380 Quévrain (BE).

(74) Agent: DEBLED, Thierry; Vesuvius Group S.A., Intel-
lectual Property Dept., Rue de Douvrain, 17, B-7011 Ghlin
(BE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted
a patent (Rule 4.17(ii)) for the following designations AE,
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ,
CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE,
EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS,
JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ,
TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM,
ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD,
SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY,
KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG,
CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT,
LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent (BF,
BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN,
TD, TG)

— as to the applicant's entitlement to claim the priority of the
earlier application (Rule 4.17(iii)) for the following desig-
nations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW,
BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ,
EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID,
IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ,
OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA,
ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ,
SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE,
IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE,
SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report
— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: REFRACTORY COMPOSITION AND PROCESS FOR THE REPAIR OF A HOT REFRACTORY WALL

(57) Abstract: The present invention relates to refractory composition consisting essentially of 40-90 dry weight % of amorphous silica aggregates, up to 40 dry weight % of alumina based compounds 10-15 dry weight % of clay, 0.2-2.0 dry weight % of a chemical binder and further containing 2 to 8% of water. These compositions are particularly useful for the repair of coke oven damaged wall in a gunning process.

WO 2004/085341 A1

Refractory composition and process for the repair of a hot refractory wall.**Description.**

[0001] The present invention relates to refractory compositions, in particular, amorphous silica based compositions, and to a process for the repair of a hot silica refractory wall using these compositions, in particular to a gunning process.

- 5 [0002] The present technico-commercial factors are pushing service life-time of coke ovens and other industrial furnaces made from silica refractory elements to their maximum. The proper maintenance and repair of such silica refractory assemblies is one of the critical points controlling their life time and continues to present severe problems, both from the standpoint of making a satisfactory repair and from interruption of or interference with production during the
- 10 repair.

[0003] The invention is particularly well adapted for repairing refractory brick liner walls of a coke oven and will be described herein with reference to coke oven repair; however, it should be understood that the invention may be employed in repairing other high temperature silica brick walls such as glass melting furnaces and is therefore not limited to use in coke ovens.

- 15 [0004] Coke ovens are normally constructed of refractory silica brick which maintain relatively high strength even at the extreme temperatures encountered in the coking operation. Such ovens may have an overall life expectancy of 40 years or more, but may nevertheless require repair after only a few years of operation. Spalling of the refractory brick in the lining wall may commence for various reasons, including small cracks resulting, for example, from foundation
- 20 settling, uneven expansion during heat-up or uncontrolled cool-down, air leaks, thermal shock and/or repeated thermal cycling during operation. The inclusion of foreign material in a coal charge can also produce "hot spots" which damage a local area. Once spalling has commenced, it can progress both to adjacent brick and more deeply into the wall until it interferes with pushing of the coke which, again, can produce more damage. Unless properly
- 25 repaired, the damage can progress through the wall liner to the heating flues.

- [0005] Since coke ovens are normally constructed in batteries each consisting of a large number of ovens extending in side-by-side relation with common walls between adjacent ovens, repair of an individual oven wall liner cannot, from a practical standpoint, be accomplished by simply cooling to ambient temperature only the oven needing repair since flues in the common
- 30 wall are required to heat the adjacent ovens. Further, any attempt to cool one oven in a battery to a temperature that would enable workmen to enter and make repairs, even if adjacent ovens were partially cooled, can result in severe stresses due to shrinking and can cause substantial damage both to the oven being repaired and to adjacent ovens. Accordingly, it has long been the practice to repair coke oven liner walls by applying a temporary patch over the damaged
- 35 area using a gunning or spraying technique wherein refractory aggregate is applied either as a slurry or in a "dry" gunning mixture which is sprayed or thrown directly onto the hot oven wall. The difficulties encountered in applying such patching material are well-known to those skilled in

the art and are generally discussed, for example, in U.S. Pat. No. 3,413,385. Particular difficulty is encountered in repairing oven liner walls by the gunning process in areas which can not conveniently be reached through an open door by repairmen, protected by a heat shield, standing outside the oven.

5 [0006] Although various techniques and procedures have been developed for repairing hot refractory walls utilizing a gunning process, the results have not always been satisfactory.

[0007] The conventional gunning technique consists in conveying the dry refractory composition to a gunning nozzle where it is mixed with water and then gunned onto the damaged wall. An important problem observed in the conventional gunning techniques is the rebound of the gunned refractory composition against the refractory wall. Attempts to solve this long known problem tend to increase the quantity of water in the gunned composition. In turn, the incorporation of large quantities of water in the coke oven chamber generates other nuisances. It has also been observed that the dry refractory composition conveyed towards the gunning nozzle is generally not perfectly homogeneous.

15 [0008] The prior art also knows semi-dry and wet gunning methods wherein the refractory composition is mixed with water before being conveyed towards the gunning nozzle. In a semi-dry gunning method, the refractory composition is premixed with a part of the necessary water by a mixer, conveyed to a special gunning nozzle, mixed with the remainder of water and then gunned through the nozzle. In a wet-gunning method, the refractory composition is premixed with all of water required for gunning, conveyed towards the gunning nozzle and then gunned. These semi-dry and wet gunning methods are generally carried out against cooled or cold walls and require particular apparatus able to convey wet refractory compositions. Further, in these methods, it is often necessary to incorporate coagulants and/or dispersing agents which in turn cause other nuisances.

25 [0009] It is an object of the present invention to provide refractory compositions with an improved homogeneity, which can be used in a conventional dry gunning apparatus and providing excellent results when used for repairing a damaged refractory wall without requiring to cool the wall in question.

[0010] It is a further object of the present invention to provide refractory compositions which, globally, require less water for gunning and do not necessitate the use of coagulants and/or dispersing agents.

30 [0011] These objects and others are reached with a refractory composition consisting essentially of 40-90 dry weight % of amorphous silica aggregates, up to 40 dry weight % of alumina based compounds, 10-15 dry weight % of clay, 0.2-2.0 dry weight % of a chemical binder and comprising further 2 to 8 % of water.

35 [0012] The quantity of clay in the composition must be comprised between 10 and 15 dry weight %. Clay provides indeed the plasticity and the sticking properties required in particular for gunning applications. If the composition comprises less than 10 dry weight % of clay, an important part of the mixture rebounds when gunned against a wall and, by way of

consequences, is lost. On the other hand, clay reduces the quality (time life, refractoriness, resistance to abrasion, ...) of the repaired wall and it is therefore preferable to avoid including more than 15 dry weight % of clay in the composition.

5 [0013] Surprisingly, it has been observed that the addition of small quantity of water in the supplied compositions comprised between 2 to 8 % of water still allow the use of conventional gunning equipment (using compressed air and a rotor system) and can be gunned against a hot wall.

10 [0014] It has also been observed that the incorporation of 2 to 8 % of water into the refractory composition allows the reduction of the quantity of water mixed with the composition in the gunning nozzle so that the global quantity of water introduced with the gunning composition is lower than with a conventional technique (6 wt. % instead of 12 wt. %).

[0015] The incorporation of water into the refractory composition permits also a better homogenisation of the composition.

15 [0016] The rebound during gunning operation is reduced at least of 50% compared to conventional techniques. This is improving the economics of the operation but this is also improving very much the health and safety work conditions for the operators as very limited dust is generated while gunning. This point is very important in regard of continuous requirements for improving the workers welfare.

20 [0017] Eventually, it has been observed that the walls repaired with the refractory composition of the invention have at least a similar life expectancy than walls repaired with conventional technique using vitreous silica based compositions.

[0018] According to a preferred embodiment of the invention, the amorphous silica aggregates comprise vitreous silica.

25 [0019] Suitable alumina based compounds comprise kyanite, andalusite, chamosite or mullite or a mixture thereof. If present, the alumina based compounds should preferably be present in a quantity comprised between 20 and 40 dry weight %.

[0020] Preferably, the chemical binder is a mineral chemical binder selected from phosphoric acid, acid alumina phosphate, alumina sulphate or sodium silicate.

30 [0021] The refractory components have preferably a grain size lower than 4 mm. I.e., at least 95 wt. % of the composition has a grain size lower than or equal to 4 mm. Preferably, 100 wt. % of the composition has a grain size lower than 5.60 mm.

[0022] Examples of preferred compositions:

Material	Example of material	Example 1 (dry wt. %)	Example 2 (dry wt. %)
Amorphous silica aggregate	Fused silica (200 μ m- 4 mm)	54.1	53.6
	Fused silica (<100 μ m)	31.6	
Alumina based compound	Kyanite (<100 μ m)		32.2
Clay		13.5	13.4
Chemical binder		0.8	0.8
Water		3.4	3.4

[0023] According to another of its objects, the present invention relates to a process for the repair of a hot refractory wall comprising the steps of

- a) conveying a refractory composition consisting essentially of 40-90 dry weight % of amorphous silica aggregates, up to 40 dry weight % of alumina based compounds, 10-15 dry weight % of clay, 0.2-2.0 dry weight % of a chemical binder and further containing 2 to 8 % of water to a gunning nozzle,
- b) mixing the said refractory composition with water in the gunning nozzle;
- c) gunning the obtained mixture against the hot refractory wall.

[0024] As indicated above, this process has shown surprising results as to the quality of the repaired wall, in particular for a coke oven wall.

Claims.

1. Refractory composition consisting essentially of 40-90 dry weight % of amorphous silica aggregates, up to 40 dry weight % of alumina based compounds, 10-15 dry weight % of clay, 0.2-2.0 dry weight % of a chemical binder and further containing 2 to 8 % of water.
2. Refractory composition according to claim 1, characterized in that the amorphous silica aggregates comprise vitreous silica.
3. Refractory composition according to claim 1, characterized in that the alumina based compounds comprise kyanite, andalusite, chamote or mullite or a mixture thereof.
4. Refractory composition according to claim 1, characterized in that the alumina based compounds content is comprised between 20 and 40 dry weight %.
5. Refractory composition according to claim 1, characterized in that the chemical binder is a mineral chemical binder selected from phosphoric acid, acid alumina phosphate, alumina sulphate or sodium silicate.
6. Refractory composition according to claim 1, characterized in that the refractory components have 95 wt. % of grain size lower than 4 mm.
7. Refractory composition according to claim 6, characterized in that the refractory components have 100 wt. % of grain size lower than 5.6 mm.
8. Process for the repair of a hot silica refractory wall comprising the steps of
 - a) conveying a refractory composition consisting essentially of 40-90 dry weight % of amorphous silica aggregates, up to 40 dry weight % of alumina based compounds, 10-15 dry weight % of clay, 0.2-2.0 dry weight % of a chemical binder and further containing 2 to 8 % of water to a gunning nozzle,
 - b) mixing the said refractory composition with water in the gunning nozzle;
 - c) gunning the obtained mixture against the hot refractory wall.
9. Process according to claim 8, characterized in that the refractory composition conveyed in step a) is a refractory composition according to any one of claims 2 to 7.
10. Process according to claim 8, characterized in that the refractory wall is a coke oven wall.

INTERNATIONAL SEARCH REPORT

International Application No

.../BE2004/000045

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B35/66 C04B35/18 F27D1/16 C10B29/06 C21C5/44

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B F27D C10B C21C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, COMPENDEX, INSPEC, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 340 782 A (LANGENOHL MARK C) 23 August 1994 (1994-08-23) column 1, line 44 - column 2, line 7; examples 2,3	1-10
A	US 4 596 601 A (RUECKL ROGER L) 24 June 1986 (1986-06-24) column 2, line 62 - column 3, line 7	1-10
A	US 4 992 397 A (HUGHES JR GUSTAV O) 12 February 1991 (1991-02-12) claim 1; example 7; table 3	1-10
A	EP 0 364 640 A (CHICAGO FIRE BRICK CO) 25 April 1990 (1990-04-25) example 4	1-10

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

Z document member of the same patent family

Date of the actual completion of the international search

19 August 2004

Date of mailing of the international search report

26/08/2004

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, TX 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Raming, T

RECU LE 12 OCT. 2004

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

.../BE2004/000045

Patent document cited in search report		Publication date	Patent family member(s)	Publication date	
US 5340782	A	23-08-1994	CA MX	2124993 A1 9405153 A1	27-01-1995 31-01-1995
US 4596601	A	24-06-1986	WO AU CA CN ES US ZA AT DE EP JP	8706224 A1 5695886 A 1233840 A1 85109463 A ,B 8706586 A1 4695323 A 8509264 A 73746 T 3684482 D1 0293365 A1 1500106 T	22-10-1987 09-11-1987 08-03-1988 03-09-1986 16-09-1987 22-09-1987 24-09-1986 15-04-1992 23-04-1992 07-12-1988 19-01-1989
US 4992397	A	12-02-1991	NONE		
EP 0364640	A	25-04-1990	US EP JP US	4780142 A 0364640 A1 2116681 A 4921536 A	25-10-1988 25-04-1990 01-05-1990 01-05-1990